

iq.ul.com



CLICK TO CONTINUE

The information presented on the UL Prospector datasheet was acquired by UL Prospector from the producer of the material. UL Prospector makes substantial efforts to assure the accuracy of this data. However, UL Prospector assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.

Component - Plastics

E256266

Guide Information

ITW ELECTRONICS COMPONENTS/ PRODUCTS (SHANGHAI) CO LTD

BLDG 5, XINZHUANG INDUSTRIAL PARK, 789 SHENFU RD, SHANGHAI 201108 CN

Formex GL-(a)(d)(f2)

Polypropylene (PP), furnished as sheets

| Color | Min. Thk (mm) | Flame Class | HWI | HAI | RTI Elec | RTI Imp | RTI Str |
|--------|---------------|-------------|-----|-----|----------|---------|---------|
| NC, BK | 0.110-0.250 | VTM-0 | 0 | 2 | 125 | - | 115 |
| | 0.38 | V-0 | 0 | 2 | 125 | - | 115 |
| | 0.43 | V-0 | 0 | 2 | 125 | - | 115 |
| | 0.71 | V-0 | 0 | 1 | 125 | - | 115 |

Comparative Tracking Index (CTI): 0

Inclined Plane Tracking (IPT) kV: -

Dielectric Strength (kV/mm): 44

Volume Resistivity (10^x ohm-cm): 16

High-Voltage Arc Tracking Rate (HVTR): 0

High Volt, Low Current Arc Resis (D495): 6

Dimensional Stability (%): -

(a) - One to three digit suffix indicating nominal thickness in mils.

(d) - May have additional suffix letter(s) indicating color.

(f2) - Subjected to one or more of the following tests: Ultraviolet Light, Water Exposure or Immersion in accordance with UL 746C, where the acceptability for outdoor use is to be determined by UL.

NOTE - HVTR, CTI and D495 are thickness independent

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2016-03-03

Last Revised: 2017-09-08

© 2018 UL LLC



| IEC and ISO Test Methods | | | | |
|--------------------------------|---------------------------|-------------------|-------------|----------------|
| Test Name | Test Method | Units | Thk (mm) | Value |
| Flammability | ISO 9773, IEC 60695-11-10 | Class (color) | 0.110-0.250 | VTM-0 (NC, BK) |
| | | | 0.38 | V-0 (NC, BK) |
| | | | 0.43 | V-0 (NC, BK) |
| | | | 0.71 | V-0 (NC, BK) |
| Glow-Wire Flammability (GWFI) | IEC 60695-2-12 | °C | - | - |
| Glow-Wire Ignition (GWIT) | IEC 60695-2-13 | °C | - | - |
| IEC Comparative Tracking Index | IEC 60112 | Volts (Max) | - | - |
| IEC Ball Pressure | IEC 60695-10-2 | °C | - | - |
| ISO Heat Deflection (1.80 MPa) | ISO 75-2 | °C | - | - |
| ISO Tensile Strength | ISO 527-2 | MPa | - | - |
| ISO Flexural Strength | ISO 178 | MPa | - | - |
| ISO Tensile Impact | ISO 8256 | kJ/m ² | - | - |
| ISO Izod Impact | ISO 180 | kJ/m ² | - | - |
| ISO Charpy Impact | ISO 179-2 | kJ/m ² | - | - |